


# Glide Smoothly

## HYDAK<sup>®</sup> Hydrophilic Coatings



### L - SERIES

## Advantages of L-Series Hydak<sup>®</sup> Coatings



Non-Crosslinked HA

**BIOCOAT**  
INCORPORATED

### BIOCOAT Inc.

211 Witmer Road  
Horsham, PA 19044  
Tel: 215-734-0888  
Fax: 215-734-0889  
www.biocoat.com

- ✓ **Lubricious:** Exhibits an extremely low surface friction
- ✓ **Biocompatible:** Made from hyaluronic acid, a natural biopolymer
- ✓ **Durable:** Able to withstand the rigors of basic invasive procedures
- ✓ **Non-thrombogenic:** Resists adsorption of fibrin and platelet adhesion
- ✓ **Hydrophilic:** Absorbs water to increase its lubricity
- ✓ **Thin:** Less than 4 microns thick!



# The HYDAK® Coating System is an excellent consideration for use in medical devices.

## Possible applications for this technology include:

- Micro catheters
- Balloons
- Guide wires
- Stents
- Blood contacting surfaces

The Hydak L-Series coatings are based on a non-crosslinked form of Hyaluronic Acid (HA) (*see illustration on the front*). This technology has applications among a gamut of fields including ophthalmology, urology, cardiology, endoscopy, and others. In particular, this coating is ideal for single-use devices that require extremely low coefficients of friction.

Coatings are composed of two layers: a polyacrylate base coat and a non-crosslinked hyaluronic acid top coat covalently bonded to the base coat. The combination can be applied to a multitude of different substrates (*see Table*). The total thickness of both layers can be as thin as 2 to 3 µm when dry, swelling to 10 µm when wet. The covalent bonding of the top coat to the base coat ensures consistent quality and physical properties.

Unlike some other coating systems, Hydak is applied via dipping, injecting, spraying, or wiping and is heat cured at temperatures in the range of 60 to 70°C. There is no photo curing equipment necessary. This produces several advantages:

- HYDAK coatings are easily applied to lumens
- UV exposure of the surface is not required
- Heat curing allows for uniform coating properties through entire cross section
- Equipment required for manufacturing is an order of magnitude less expensive

HYDAK Coating Adhesion to Various Substrates (ASTM D3359-78, Method B)

Substrate	Base Coat in Organic Solvent	Base Coat in Aqueous Dispersion
HDPE	Excellent*	
LDPE	Excellent*	
Nylon 12	Excellent*	Poor
Nylon 6	Excellent*	
Nylon 66	Excellent*	Excellent
70D Pebax	Excellent	Poor
55D Pebax	Excellent	Poor
35D Pebax	Good	Excellent
90A Polyurethane	Poor	Excellent
60A Polyurethane	Excellent	
PEEK	Excellent	Excellent
PET	Excellent	Excellent
PMMA	Excellent	
Polycarbonate	Not Recommended	Excellent*
Polypropylene	Good*	
PVC	Excellent	Excellent
Silicone	Good*	Poor
Stainless Steel	Good	Excellent
Tygon	Not Recommended	Excellent
FEP	Poor	Poor
Teflon	Poor	Poor

\* With plasma treatment



## About Biocoat

Biocoat, Inc. is based in Horsham, Pennsylvania with core competencies focusing on coatings development and licensing. The company works with its clients to tailor its HYDAK® and other coating technologies to specific surfaces, and acts as a support network for development and manufacturing throughout the project/product life cycle.